



# CHEMBLOC SERIES 237SC

## PRODUCT PROFILE

**GENERIC DESCRIPTION** Modified Polyamine Epoxy

**COMMON USAGE** A multi-purpose resin for fiberglass reinforced mat (65 mils) or mortar/fiberglass reinforced mat (125 mils) secondary containment systems. Protects against chemicals, thermal cycling, impact and abrasion.

**COLORS** 00GR Gray. Color may not be uniform and is not intended to be finish coat—see Topcoats listed below. **Note:** Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats. Epoxies will stain with extended exposure to certain acids. As a result, darker colors are recommended.

## COATING SYSTEM

**SURFACER/FILLER/PATCHER** Series 215, 218. **Note:** A repair kit of 201, with Part C fumed silica, is available for small patching/surfacing repairs (reference Technical Bulletin 99-22). For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.

**PRIMERS** Self-priming or Series 201

**FLEXIBLE BASECOAT** Series 206SC (optional replacement for Series 237SC and 239SC mortar/slurry basecoat). Reference the appropriate product data sheet for additional information.

**TOPCOATS** Series 120, 280, 282, 252SC. **Note:** A saturant coat of 237SC liquids is required over fiberglass mat prior to application of topcoat.

## SURFACE PREPARATION

Prepare surfaces by method suitable for exposure and service. Refer to the appropriate primer data sheet for specific recommendations. When self priming:

**CONCRETE** Allow new concrete to cure 28 days. Verify dryness by testing for moisture with a “plastic film tape-down test” (Reference ASTM D 4263). Should moisture be detected, perform “Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride” (Reference ASTM F 1869). Moisture content not to exceed three pounds per 1,000 sq ft in a 24 hour period. Abrasive blast or equivalent to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide surface profile (Reference SSPC-SP13/NACE 6, ICRI CSP5). Large voids, bugholes and other cavities should be filled with recommended filler or surfacer.

**ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

**VOLUME SOLIDS** 100% (mixed)

**RECOMMENDED DFT** **Primer:** 4.0 to 12.0 (100-305 microns) per coat.  
**Resinous Basecoat:** 6.0 to 12.0 mils (150-305 microns).  
**Mortar/Slurry Basecoat:** 60 to 80 mils.  
**Saturant:** 8.0 to 12.0 mils (200-305 microns).

CURING TIME	Temperature	To Topcoat	Place in Service	Full Cure
	75°F (24°C)	8 to 24 hours	24 hours	5 days

If more than 24 hours have elapsed between coats, the ChemBloc coated surface must be mechanically abraded before topcoating. **Note:** A 24 hour cure provides for traffic, secondary containment and certain mild chemical exposures. Up to five days cure is required for certain severe chemical exposures. Contact your Tnemec representative or Tnemec Technical Services.

**VOLATILE ORGANIC COMPOUNDS** **Unthinned:** 0.25 lbs/gallon (30 grams/litre)  
**Thinned 10%:** 0.89 lbs/gallon (106 grams/litre)

**HAPS** **Unthinned:** 0.0 lbs/gal solids  
**Thinned 10%:** 0.7 lbs/gal solids

**THEORETICAL COVERAGE** 1,604 mil sq ft/gal (39.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

**NUMBER OF COMPONENTS** Resin Containment Kit (RCK)—Two: Part A (epoxy) and Part B (amine)  
Mortar Containment Kit (MCK)—Three: Parts A (epoxy), B (amine) and C (aggregate)

PACKAGING	PART A	PART B	PART C	Yield (mixed)
RCK	1-1 gallon can	1-1/2 gallon can	N/A	1.5 gallons
MCK	1-1 gallon can	1-1/2 gallon can	1-30 lb bag	3 gallons

**Note:** The fiberglass reinforcing mat (S211-0215) is calculated per sq ft based on a 38 in x 500 ft (1,500 sq ft) roll and is available in full rolls only. (Sold separately for both kit sizes.)

**NET WEIGHT PER GALLON** 9.10 ± 0.25 lbs (4.13 ± .11 kg) (Parts A & B mixed)

**STORAGE TEMPERATURE** Minimum 50°F (10°C) Maximum 90°F (32°C)  
Material should be stored at temperatures between 70°F and 90°F (21°C and 32°C) for at least 48 hours prior to use.

**TEMPERATURE RESISTANCE** (Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

**SHELF LIFE** 12 months at recommended storage temperature.

**FLASH POINT - SETA** N/A

**HEALTH & SAFETY** This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

# CHEMBLOC | SERIES 237SC

## APPLICATION

**COVERAGE RATES** Before commencing, obtain and thoroughly read the Secondary Containment Installation and Application Guide.

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Kit (m <sup>2</sup> /Kit)
Primer (RCK)	4.0-12.0 (100-305)	4.0-12.0 (100-305)	201-602 (18.6-55.9)
Resinous Basecoat (RCK)	6.0-12.0 (150-305)	6.0-12.0 (150-305)	201-401 (18.6-37.3)
Mortar/Slurry Basecoat (MCK) †	60.0-80.0 (1525-2030)	60.0-80.0 (1525-2030)	61-81 (5.6-7.5)
Saturant Coat (RCK)	8.0-12.0 (205-305)	8.0-12.0 (205-305)	201-301 (18.6-27.9)

† Coverage rates are based on the addition of the entire Part C filler.

**MIXING** Use a variable speed drill with a box blade. Slowly mix Part A component, and while under agitation add Part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula. **Note:** A large volume of material will set up quickly if not applied or reduced in volume. **Caution: Do not reseal mixed material. An explosion hazard may be created.**  
**Mortar/Slurry Basecoat:** If a filled basecoat mortar is required, slowly add one 30 lb bag of Part C filler (S211-0214) to mixed liquids until all the Part C filler is thoroughly blended. The yield will be approximately 3 gallons. For filled basecoat slurry, the Part C filler can be reduced by approximately 6 lbs or 20%.

**THINNING** Normally not required. Saturant coat may be thinned up to 10% with No. 2 Thinner.

**POT LIFE** 30 to 35 minutes at 75°F (24°C)  
 Increasing material temperatures will significantly reduce the pot life.

**APPLICATION** **Primer:** 4.0-12.0 dry mils (100-305 microns), 4.0-12.0 wet mils (100-305 microns), 201-602 sq ft/kit (18.6-55.9 m<sup>2</sup>).  
**Fiberglass Mat Reinforced Application (RCK):** Uniformly roller apply the mixed liquids (Parts A and B) at a rate of 6.0-12.0 mils or a rate of 201-401 sq ft/kit (18.6-37.3 m<sup>2</sup>).  
**Mortar/Fiberglass Mat Reinforced Application (MCK):** Uniformly trowel apply the mixed Part A and Part B liquids and Part C filler (S211-0214) at a rate of approximately 60-80 mils or 61-81 sq ft/kit (5.6-7.5 m<sup>2</sup>), leaving a smooth, even finish.  
**Reinforcement and Saturant:** While the basecoat is still wet, lay and press the fiberglass reinforcing mat (S211-0215) into the surface. Using a rib roller, backroll fiberglass to remove any air pockets. Once mat is placed, immediately saturate mat with Series 237SC saturant coat (approximately 8.0 to 12.0 mils or 201-301 sq ft/kit) until fiberglass mat is completely wet out. **Caution: The saturant coat should be applied at a thickness to only wet out the fiberglass mat. Any attempt to build a film on top of the mat may result in sags and runs.**

**APPLICATION EQUIPMENT** **Primer, Resinous Basecoat and Saturant:** Brush, roller, squeegee. Brush small areas only. A rib roller or broad knife should be used to press and embed fiberglass reinforcing mat in both the resin and aggregate filled basecoat.  
**Mortar/Slurry Basecoat:** Squeegee, trowel, loop roller.  
**Note:** For detailed instructions, refer to the Secondary Containment Installation and Application Guide.

**SURFACE TEMPERATURE** Minimum of 55°F (13°C), optimum 65°F to 80°F (18°C to 27°C), maximum of 90°F (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

**MATERIAL TEMPERATURE** For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.

**CLEANUP** Flush and clean all equipment immediately after use with xylene or MEK.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.