

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

SPECIFIER NOTE

This specification is provided by Mid-Atlantic Coatings, Inc. as a service and is intended to be used as a guideline for preparing a project specific specification section. Every heading may not be needed. Delete headings not used and renumber remaining used headings to be numerically correct. Contact Mid-Atlantic Coatings or Tnemec Company before using this specification for any product updates.

PART 1 - GENERAL

1.1 RELATED DOCUMENTS

- A. This Section includes shop and field surface preparation and shop and field painting of various substrates.
 - 1. Surface preparation, including in the shop and applications of metal primer, and field applications of primers and finishes are specified in this Section.
- B. Drawings and general provisions of the Contract, including General and Supplementary Conditions and Division 1 Specification Sections, apply to this Section.

1.2 SUMMARY

- A. This Section includes surface preparation and application of high-performance coating systems on the following substrates:
 - 1. Exterior Substrates:
 - a. Steel Structures
 - b. Miscellaneous & Ornamental Metals
 - c. Galvanized & Non-Ferrous Metals
- B. Related Sections include the following:
 - 1. Division 1 Section "LEED Green Building Summary, Requirements, and Goals" for additional LEED requirements.
 - 2. Division 5 Sections for shop priming of metal substrates with primers specified in this Section.
 - 3. Division 9 Section "Painting" for general field painting.

1.3 SUBMITTALS

- A. Product Data: For each type of product indicated.
- B. Samples for Initial Selection: For each type of finish-coat product indicated.
- C. Samples for Verification: For each type of coating system and in each color and gloss of finish coat indicated.
 - 1. Submit Samples on rigid backing, 8 inches square.
 - 2. Step coats on Samples to show each coat required for system.

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

3. Label each coat of each Sample.
 4. Label each Sample for location and application area.
- D. Product List: For each product indicated. Cross-reference products to coating system and locations of application areas. Use same designations indicated on Drawings and in schedules.
- E. LEED Submittals: For Credit EQ 4.2, manufacturers' product data for coatings, including printed statement of VOC content and chemical components.

1.4 QUALITY ASSURANCE

A. Material Performance Criteria:

1. Products: Provide certified test reports when submitting products other than those specified herein the specification. Test reports shall indicate the test method, system and requirements for those products being submitted, and shall meet or exceed the test criteria and performance values of the specified coatings herein.

B. Applicator Qualifications:

1. Preparation and Workmanship: A firm or individual with a minimum of (5) years experienced in applying coatings similar in material design, and extent to those indicated for a particular project, whose work has resulted in applications with a record of successful in-service performance.

C. Mockups: Apply benchmark samples of each coating system indicated to verify preliminary selections made under sample submittals and to demonstrate aesthetic effects and set quality standards for materials and execution.

1. Architect will select one surface to represent surfaces and conditions for application of each type of coating and substrate.
 - a. Wall and Ceiling Surfaces: Provide samples of at least 100 sq. ft.
 - b. Other Items: Architect will designate items or areas required.
2. Apply benchmark samples after permanent lighting and other environmental services have been activated.
3. Final approval of color selections will be based on benchmark samples.
4. If preliminary color selections are not approved, apply additional benchmark samples of additional colors selected by Architect at no added cost to Owner.
5. Approved mockups may become part of the completed Work if undisturbed at time of Substantial Completion.

1.5 DELIVERY, STORAGE, AND HANDLING

A. Deliver materials to project site in manufacturer's original, unopened packages and containers bearing manufacturer's name and label and the following information.

1. Product name or title of material.

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

2. Product description (generic classification or binder type)
3. Manufacturer's stock number and date of manufacture.
4. Contents by volume, for pigment and vehicle constituents.
5. Thinning instructions.
6. Application instructions.
7. Color name and number.
8. VOC content.

B. Store materials not in use in tightly covered containers in well-ventilated areas with ambient temperatures continuously maintained at not less than 45 deg F.

1. Maintain containers in clean condition, free of foreign materials and residue.
2. Remove rags and waste from storage areas daily.

1.6 PROJECT CONDITIONS

- A. Apply coatings only when temperature of surfaces to be coated and surrounding air temperatures are between 50 and 95 deg F.
- B. Do not apply coatings in snow, rain, fog, or mist; when relative humidity exceeds 85 percent; at temperatures less than 5 deg F above the dew point; or to damp or wet surfaces.

1.7 PRODUCT WARRANTY

- A. Provide manufacturer's (10) year color and gloss, crack, check, peel warranty at the completion of the project.

PART 2 - PRODUCTS

2.1 MANUFACTURERS

- A. Materials specified are those that have been evaluated for the specific service on this project. Products of the Tnemec Company, Inc. are listed to establish a standard of quality. Equivalent materials of other manufacturer's may be submitted a minimum ten days prior to bid date on written approval of the Architect.
- B. Materials specified herein shall not preclude consideration of equivalent or superior materials. Requests for substitution shall be submitted to the architect a minimum ten days prior to bid date in accordance with the general construction documents and in compliance with substitution procedures in Section 01 60 00 of this Project Manual.
 1. Requests for substitution shall include evidence of satisfactory past performance on substrates that are listed herein.
 2. Substitutions will not be considered that change the generic type, number of coats or do not meet specified total dry film thickness.
- C. Colors: As selected by Architect from manufacturer's full range.

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

2.2 HIGH PERFORMANCE COATINGS – GENERAL REQUIREMENTS

- A. Materials Compatibility: Provide shop and field primers, and finish-coat materials that are single source and compatible with one another and with the substrates indicated under conditions of service and application, as demonstrated by manufacturer based on testing and field experience.
- B. Paints and Coatings - General:
 - 1. Unless otherwise indicated, provide factory thinned coatings. Mix coatings to correct ratio and consistency in accordance with manufacturer's instructions before application. Do not reduce, thin, or dilute coatings or add materials to coatings unless such a procedure is specifically described in manufacturer's product instructions. VOC numbers used in this document need to be confirmed by using the products MSDS sheets.
 - 2. Requirements: USGBC Version LEED 3 (v3), and EQ 4.2 Low-Emitting Materials; Paints & Coatings.
 - 3. Paints and coatings used on the interior of the building (defined as inside of the weatherproofing system and applied on-site) shall comply with the following criteria:
 - a. Coating Type: VOC weight in grams/liter of product minus water
 - b. Non-flat: 150 g/L
 - c. Flat: 50 g/L
 - d. Anti-Corrosive Primer & Paint: 250 g/l
- C. CARB/VOC Requirements
 - 1. Industrial & Exterior – 250 g/l

2.3 SHOP/FIELD PRIMERS

- A. Tnemec Series 27 WB Typoxy (Galvanized Metal Primer & Touch-up)
 - 1. Generic Type: Inorganic Hybrid Water-Based Epoxy
 - 2. Finish: Flat
 - 3. Properties:
 - a. Solids by Volume: 90.0 +/- 2.0%
 - b. VOC: 0.10 lbs/gallon (11 grams/litre)
 - 4. Performance Criteria:
 - a. Abrasion: ASTM D 4060, (CS-17 Wheel, 1,000 grams load). No more than 175 mg loss after 1,000 cycles.
 - b. Adhesion: ASTM D 3359, (Method B, mm Crosshatch). No less than a rating of 5.
 - c. Humidity: ASTM D 4585. No blistering, cracking, rusting or delamination of film after 4,500 hours exposure.
 - d. Salt Spray (FOG). ASTM B 117. No blistering, cracking, rusting or delamination of film after 6,000 hours.
 - e. Immersion: ASTM D 870. No blistering, cracking, rusting or delamination of film after 2,000 hours.

SECTION 09 97 13. 13
 EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
 FLUOROPOLYMER COATING

2.4 FLUOROPOLYMER COATING

A. Advanced Thermoset Solution Fluoropolymer, Pigmented & Metallic Coating (Exterior Metals)

1. Product: Tnemec Series 1071 Fluoronar (Exterior Finish Coat)
2. Finishes:
 - a. Series 1070V - gloss
 - b. Series 1071V - Semi-gloss
 - b. Series 1072V – Satin
 - c. Series 1078 – Metallic
3. Properties:
 - a. Solids by Volume: 60.0 +/- 2.0%
 - b. VOC:
 - i) Series 1070V: 0.83 lbs/gallon (99 grams/litre)
 - ii) Series 1071V: 0.81 lbs/gallon (97 grams/litre)
 - iii) Series 1072V: 0.77 lbs/gallon (93 grams/litre)
 - iii) Series 1078: 54.0+/- 2.0% (400 grams/litre)
4. Performance Criteria:
 - a. Abrasion: ASTM D4060, (CS-17 Wheel, 1,000 grams load). No more than 103 mg loss after 1,000 cycles.
 - b. Adhesion: ASTM D 4541 (Method B, Type II Tester). No less than 1,333 psi (9.19 MPa) pull, average of three tests.
 - c. Adhesion: ASTM D 4541 (Method E, Type V Tester). No less than 1,930 psi (13.3 MPa) pull, average of three tests.
 - d. Exterior Exposure: Exposed at 45 degrees facing south. No blistering, cracking, rusting or delamination of film. No less than 87% gloss retention (8.9 units gloss change) and 2.99 DED FMCI (MacAdam units) color change after 24 months.
 - e. Exterior Exposure: ASTM D 4141, Method C (EMMAQUA). No blistering, cracking or chalking. No less than 96% gloss retention (3.2 units gloss change) and 0.18 DED Hunter Lab color change after 1,260 M/J m2 EMMAQUA exposure, average of five tests in five colors.
 - f. Flexibility: ASTM D 522 (Method A – Conical Mandrel). No less than 14.83% elongation average of three tests.
 - g. Graffiti Resistance: The following graffiti materials applied to coating and allowed to 7 days.

<u>Reagent</u>	<u>Series 680</u>	<u>Xylene</u>	<u>MEK</u>
Acrylic Spray Paint	Removal	Removal	Removal
Epoxy Spray Paint	Removal	Removal	Removal
Markette Marker	Removal	Removal	Removal
Ball Point Ink	Removal	Removal	Removal
Crayon	Removal	Removal	Removal
Lipstick	Removal	Removal	Removal

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

Some slight gloss loss and/or softening may occur depending on the amount of effort required for removal of the graffiti and length of exposure of the underlying coating to the cleaning solvents.

- h. Hardness: ASTM D 3363. No gouging or scratching with an 8H or less pencil.
- i. Humidity: ASTM D 4585. No blistering, cracking, rusting or delamination of film after 3,000 hours exposure.
- j. Impact: ASTM D 2794. No visible cracking or delamination of film after 34.6 inch/pounds (3.9J) or less direct impact.
- k. QUV: ASTM D 4587 (UVA-340 Bulbs, Cycle 4:8 hours UV/4 hours condensation). No blistering, cracking, or chalking. No less than 93% gloss retention (5.7 units gloss change) and 2.21 DED FMCII (MacAdam Units) color change after 10,000 hours exposure, average of five tests in five colors. No blistering, cracking, or chalking. No less than 60% gloss retention (31.4 units gloss change) and 1.89 DED FMCII (MacAdam Units) color change after 25,000 hours exposure, average of five tests in five colors.
- l. Salt Spray (Fog): ASTM B 117. No blistering, cracking, rusting or delamination of film. No more than 1/32 inch rust creepage at scribe after 10,000 hours exposure. No blistering, cracking, rusting or delamination of film. No more than 1/8 inch rust creepage at scribe after 10,000 hours exposure. No blistering, cracking, rusting or delamination of film. No more than 1/16 inch rust creepage at scribe after 10,000 hours exposure.
- m. Weatherometer Exposure: ASTM D 5031. No blistering, cracking, or chalking. No less than 92% gloss retention (6 units gloss change) and 0.73 DED Hunter Lab Scale color change after 5,000 hours exposure.

2.5 SHOP SURFACE PREPARATION ¹⁾

- A. Exterior/Interior Galvanized Metals – (Non- Quenched or Non-Passivated Galvanized)
 - a. Exterior/Severe Exposure/Wet/Chemical – ASTM D 6386 & SSPC SP7 Brush-Off Blast Cleaning. Uniformly abrade & profile the surface using fine abrasive and low pressure blast method to minimize damage to the galvanized metal.
 - b. Interior Exposed/Mild – SSPC SP1 Solvent Cleaning & Chemical Etching (Clean N’ Etch by Great Lakes Laboratories or equal)
- B. Exterior/Interior Galvanized Metals – (Quenched or Passivated Galvanized)
 - a. ASTM D 6386 & SSPC SP7 Brush-Off Blast Cleaning. Uniformly abrade & profile the surface using fine abrasive and low pressure blast method to minimize damage to the galvanized metal.

2.6 SHOP APPLIED PRIMER

- A. Exterior & Interior Galvanized Metals
 - a. Galvanized Metals – Series 27 W.B. Typoxy applied at 2.5 to 3.5 mils DFT

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

SPEC WRITER NOTE

¹⁾ *Coordinate shop cleaning and primer in the one or more of the following; Section 05 10 00 Structural Steel, Section 05 50 00 Metal Fabrications, Section 05 70 00 Ornamental Metals or Section 05 08 00 Factory-Applied Metal Coatings.*

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Examine substrates and conditions, with Applicator present, for compliance with requirements for maximum moisture content and other conditions affecting performance of work.
 - 1. Verify compatibility with and suitability of substrates, including compatibility with existing finishes or primers.
 - 2. Begin coating application only after unsatisfactory conditions have been corrected and surfaces are dry.
 - 3. Coating application indicates acceptance of surfaces and conditions.

3.2 FIELD PREPARATION

- A. Comply with manufacturer's written instructions and recommendations.
- B. Galvanized & Non-Ferrous Metals (Non- Quenched or Non-Passivated Galvanized)
 - a. Exterior/Severe Exposure/Wet/Chemical – ASTM D 6386 & SSPC SP7 Brush-Off Abrasive Blast Cleaning – Uniformly scarify & profile the surface using a fine abrasive and low pressure blast while minimizing damage to the galvanized metal.
 - b. Interior Exposed/Mild – SSPC SP1 Solvent Cleaning & Chemical Etching (Clean N' Etch by Great Lakes Laboratories or equal)
- C. Exterior/Interior Galvanized Metals – (Quenched Galvanized)
 - a. ASTM D 6386 & SSPC SP7 Brush-Off Abrasive Blast Cleaning – Uniformly scarify & profile the surface using a fine abrasive and low pressure blast while minimizing damage to the galvanized metal.

3.3 APPLICATION

- A. Apply high-performance coatings according to manufacturer's written instructions.
 - 1. Use applicators and techniques suited for coating and substrate indicated.
 - 2. Coat surfaces behind movable equipment and furniture same as similar exposed surfaces. Before final installation, coat surfaces behind permanently fixed equipment or furniture with prime coat only.
 - 3. Coat back sides of access panels, removable or hinged covers, and similar hinged items to match exposed surfaces.

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

- B. Tint each undercoat a lighter shade to facilitate identification of each coat if multiple coats of the same material are to be applied. Tint undercoats to match color of finish coat, but provide sufficient difference in shade of undercoats to distinguish each separate coat.
- C. If undercoats or other conditions show through final coat, apply additional coats until cured film has a uniform coating finish, color, and appearance.
- D. Apply coatings by spray application to produce surface films without cloudiness, spotting, holidays, laps, brush marks, runs, sags, ropiness, or other surface imperfections. Produce sharp glass lines and color breaks.

3.4 FIELD QUALITY CONTROL

- A. Owner reserves the right to invoke the following procedure at any time and as often as Owner deems necessary during the period when coatings are being applied:
 - 1. Owner will engage the services of a qualified testing agency to sample coating material being used. Samples of material delivered to Project site will be taken, identified, sealed, and certified in presence of Contractor.
 - 2. Testing agency will perform tests for compliance with specified requirements.
 - 3. Owner may direct Contractor to stop applying coatings if test results show materials being used do not comply with specified requirements. Contractor shall remove noncomplying coating materials from Project site, pay for testing, and recoat surfaces coated with rejected materials. Contractor will be required to remove rejected materials from previously coated surfaces if, on recoating with complying materials, the two coatings are incompatible.

3.5 CLEANING AND PROTECTION

- A. At end of each workday, remove rubbish, empty cans, rags, and other discarded materials from Project site.
- B. After completing coating application, clean spattered surfaces. Remove spattered coatings by washing, scraping, or other methods. Do not scratch or damage adjacent finished surfaces.
- C. Protect work of other trades against damage from coating operation. Correct damage by cleaning, repairing, replacing, and recoating, as approved by Architect, and leave in an undamaged condition.
- D. At completion of construction activities of other trades, touch up and restore damaged or defaced coated surfaces.

3.6 HIGH-PERFORMANCE COATING SCHEDULE

- A. Exterior Galvanized and Non-Ferrous Metals ¹⁾
 - 1. Fluoropolymer, Pigmented Coating, Exterior
 - a. Shop/Field Primer: Series 27-color W.B. Typoxy, applied at 2.0 to 3.0 mils DFT

SECTION 09 97 13. 13
EXTERIOR GALVANIZED METAL/STEEL/NON-FERROUS
FLUOROPOLYMER COATING

SPEC WRITER NOTE

- ¹⁾ List Surface Preparation and shop primer for Steel & Galvanized Metal Substrates in one or more of the following; Section 05 10 00 Structural Steel, Section 05 50 00 Metal Fabrications, Section 05 70 00 Ornamental Metals or Section 05 08 00 Factory-Applied Metal Coatings.
- b. Touch-up: Apply Series 1 Omnithane to damaged galvanized metals, applied at 2.5 to 3.5 mils DFT
 - c. First Coat: Series 27-color W.B. Typoxy, applied at 2.0 to 3.0 mils DFT
 - d. Series 1071V-color Fluoronar, applied at 2.0 to 3.0 mils [1070V, gloss] [1071V,semi-gloss] [1072V, satin] [1078, metallic]

SPEC WRITER NOTE

- ¹⁾ *If Series 1078 is selected a clear coat of [Series 1079, gloss] [1079-0762, Semi-Gloss] or [1079-0763, Satin] is required for warranty protection.*

END OF SECTION 09 97 13. 23